



Europäisches Patentamt  
European Patent Office  
Office européen des brevets

Publication number:

**0 277 606  
A2**

## EUROPEAN PATENT APPLICATION

Application number: **88101320.5**

Int. Cl. 4: **H01L 23/52**, **H01L 25/04**,  
**H01L 21/60**

Date of filing: **29.01.88**

Priority: **02.02.87 US 9981**

Date of publication of application:  
**10.08.88 Bulletin 88/32**

Designated Contracting States:  
**DE FR GB IT**

Applicant: **International Business Machines Corporation**  
**Old Orchard Road**  
**Armonk, N.Y. 10504(US)**

Inventor: **Gazdik, Charles Edward**  
**911 Westminster Road**  
**Endicott, N.Y. 13760(US)**  
Inventor: **McBride, Donald Gene**  
**2058 Cheshire Road**  
**Binghamton, N.Y. 13903(US)**  
Inventor: **Seraphim, Donald Phillip**  
**400 Rano Blvd.**  
**Vestal, N.Y. 13850(US)**  
Inventor: **Toole, Patrick Albert**  
**20 Harborview Rd.**  
**Westport, CT 06880(US)**


Representative: **Teufel, Fritz, Dipl.-Phys. et al**  
**IBM Deutschland GmbH Europäische**  
**Patentdienste Postfach 22 00 26**  
**D-8000 München 22(DE)**

**Full panel electronic packaging structure and method of making same.**

An electronic packaging structure (1), and a method of making this structure, are disclosed. The electronic packaging structure comprises a full panel, circuitized flexible film semiconductor chip carrier (2) mounted on a circuitized substrate (6) such as a printed circuit board. A plurality of semiconductor chips (4) are mounted on the carrier in a selected pattern, and the carrier, with the chips, is mounted on a matching pattern of bonding sites on the circuitized substrate. Preferably, the circuitized flexible film semiconductor chip carrier is manufactured on a support structure used to facilitate handling of the circuitized flexible film and to facilitate heat transfer from the semiconductor chips mounted on the carrier to a heat sink (20) which is part of the circuitized substrate. Also, the semiconductor chips mounted on the flexible film chip carrier may be tested, and

burned in, while on the support structure before the chip carrier, with the chips, is mounted on the circuitized substrate.

FIG. 2



## FULL PANEL ELECTRONIC PACKAGING STRUCTURE AND METHOD OF MAKING SAME

### BACKGROUND OF THE INVENTION

The present invention relates to electronic packaging, and, more particularly, relates to structures for electronic packaging of semiconductor chips, and to methods for making such electronic packaging structures.

Typically, semiconductor chips are mounted on circuitized substrates, known as semiconductor chip carriers, having electrical circuit lines for connecting the chip to a printed circuit board, or other such electronic structure, which may be used as part of a computer, or other such equipment. For example, in many applications, it is desirable to mount several semiconductor chip carriers, each housing at least one semiconductor chip, on one printed circuit board. Typically, the several semiconductor chip carriers, with their semiconductor chips, are interconnected electrically by the circuitry of the printed circuit board.

In a relatively high volume manufacturing environment, there is a need to reliably and cost-effectively manufacture such printed circuit boards, and other such structures, with a plurality of semiconductor chips mounted thereon. These manufacturing goals become increasingly more difficult to reach as the number and complexity of the semiconductor chips which it is desired to mount on one printed circuit board, or other such structure, increases.

### SUMMARY OF THE INVENTION

Therefore, an object of the present invention is to provide an electronic packaging structure for reliably and cost-effectively mounting a plurality of electronic devices on a printed circuit board or other such structure.

Another object of the present invention is to provide a method for making such an electronic packaging structure which is suitable for use in a relatively high volume manufacturing environment.

These and other objects of the present invention are attained by an electronic packaging structure comprising a full panel flexible film chip carrier having a plurality of semiconductor chips, or other such electronic devices, mounted thereon in a selected pattern. This full panel flexible film chip carrier is mounted on a circuitized substrate, such as a printed circuit board, having a plurality of bonding sites, electrically interconnected by the circuit lines of the substrate, and arranged in a pattern which matches the pattern of the semicon-

ductor chips mounted on the full panel flexible film chip carrier. Preferably, the full panel flexible film chip carrier is an integral, flexible sheet of polyimide sized to cover all of the bonding sites on the circuitized substrate, and having circuitry on at least one side with lands for interconnecting the circuitry of the polyimide layer to the bonding sites on the circuitized substrate.

The foregoing electronic packaging structure is especially suited for manufacture in a relatively high volume manufacturing environment by a method which comprises mounting a full panel circuitized flexible film, with a plurality of electronic devices mounted thereon in a selected pattern, to a circuitized substrate having a plurality of bonding sites, electrically interconnected with circuit lines, and arranged in a pattern which matches the pattern of the electronic devices on the circuitized flexible film. Preferably, the circuitized flexible film is formed on a support structure which may be used to facilitate handling of the circuitized flexible film before it is mounted on the circuitized substrate, and which may be used to facilitate heat transfer from the electronic devices mounted on the circuitized flexible film to a heat sink which is part of the circuitized substrate. Also, preferably, the electronic devices mounted on the circuitized flexible film are tested and burned in while on the support structure before the circuitized flexible film is mounted on the circuitized substrate.

### BRIEF DESCRIPTION OF THE DRAWING

Other objects and advantages of the present invention will be apparent from the following description in conjunction with the accompanying drawing, in which like reference numerals identify like elements, and in which:

Figure 1 is a perspective view of an electronic packaging structure in accordance with the principles of the subject invention, comprising a full panel circuitized flexible film with a plurality of semiconductor chips mounted on a printed circuit board.

Figure 2 is a cross-sectional view taken along line A-A of the electronic packaging structure shown in Figure 1.

Figure 3 is a perspective view of the full panel circuitized flexible film with the plurality of semiconductor chips shown in Figure 1.

Figure 4 is a perspective view of the printed circuit board shown in Figure 1.

## DESCRIPTION OF THE PREFERRED EMBODIMENT

Referring to Figure 1, a perspective view is shown of an electronic packaging structure 1 in accordance with the principles of the present invention. As shown in Figure 1, the electronic packaging structure 1 comprises a full panel, circuitized, flexible film 2 attached to a frame 8 with a plurality of semiconductor chips 4 in a selected pattern mounted on a printed circuit board 6 made of a dielectric material, such as glass cloth impregnated with epoxy resin. If desired, the circuit board 6 may be a multilayer structure having several signal planes, ground planes, etc. For clarity, the circuitry on the flexible film 2, and the circuitry on the printed circuit board 6, have not been shown in Figure 1. Also, for ease of illustration, no attempt has been made to draw to scale the electronic packaging structure 1 shown in Figure 1 or the structures shown in the other Figures.

Figure 2 is a cross-sectional view taken along line A-A of the electronic packaging structure 1 shown in Figure 1. Figure 2 shows portions of the circuit lines 10 on the flexible film 2 and portions of the circuit lines 12 on the circuit board 6. Also, Figure 2 shows interconnections 14 between lands 24 of the circuit lines 12 on the circuit board 6 and lands 22 of the circuit lines 10 on the flexible film 2. In addition, Figure 2 shows interconnections 16 (solder balls which are part of controlled collapse chip connections (C-4)) between pads 21 of the circuit lines 10 on the flexible film 2 and terminals 18 of the semiconductor chips 4. For ease of illustration in Figure 2, only a portion is shown of each of the circuit lines 10 on the flexible film 2, and of each of the circuit lines 12 on the circuit board 6. Figure 2 also shows a heat sink 20 which is part of the circuit board 6, and heat conducting vias 19 filled with a heat conducting material, such as copper, for conducting heat from the flexible film 2 to the frame 8 and the heat sink 20.

Referring to Figure 3, a perspective view is shown of the full panel, circuitized, flexible film 2 attached to the frame 8 with the plurality of semiconductor chips 4 mounted thereon in the selected pattern shown in Figure 1. Figure 3 also shows the circuit lines 10 on top of the flexible film 2 which is attached to the top of the frame 8, and the heat conducting vias 19, filled with copper, in the flexible film 2. The semiconductor chips 4 are mounted on the pads 21 (see Figure 2) of the circuit lines 10 through the interconnections 16 (also shown in Figure 2) which physically and electrically connect the semiconductor chips 4 to the circuit lines 10 on the flexible film 2. Figure 3 also shows the lands 22 of the circuit lines 10 used in connecting the circuit lines 10 on the flexible film 2 to the lands 24 of the

circuit lines 12 on the circuit board 6 (also, see Figures 2 and 4). For clarity, only some of the lands 22 and circuit lines 10 in Figure 3 have been labelled. Figure 1 shows the flexible film 2 with the semiconductor chips 4 mounted on the top surface of the circuit board 6.

Figure 4 is a perspective view of the printed circuit board 6 shown in Figure 1. Figure 4 shows the circuit lines 12 on the printed circuit board 6 with the lands 24 forming bonding sites 25 arranged in a pattern which matches the pattern of the semiconductor chips 4 mounted on the flexible film chip carrier 2. The bonding sites 25 are the locations where the circuit lines 12 on the printed circuit board 6 are connected to the circuit lines 10 on the flexible film 2. For clarity and ease of illustration, in Figure 4, only a portion of each of the circuit lines 12 on the printed circuit board 6 is shown, and only some of the lands 24 and the circuit lines 12 have been labelled. However, it should be noted that, preferably, the circuit lines 12 on the printed circuit board 6 electrically interconnect the lands 24 of different bonding sites 25 thereby electrically interconnecting the semiconductor chips 4 on the full panel, circuitized, flexible film 2 when the film 2 with the chips 4 is mounted on the circuit board 6.

Preferably, the flexible film 2 attached to the frame 8 shown in Figures 1, 2, and 3, is a relatively thin sheet of polyimide. For example, the flexible film 2 may be a sheet of polyimide having a thickness between approximately 5.1 to 7.6 microns (about 0.0002 to 0.0003 inch), a width of approximately 177.8 millimeters (about 7 inches), and a length of approximately 228.6 millimeters (about 9 inches). For most applications, the polyimide should have a thickness of less than approximately 12.7 microns (about 0.0005 inch) to provide stress relief during thermal cycling of the polyimide when manufacturing and using the electronic packaging structure 1. However, the polyimide should not be so thin that it loses its structural integrity such that the polyimide cannot function as a structurally continuous dielectric layer. For some applications, it may be desirable for the polyimide layer 2 to have a thickness between approximately 12.7 and 25.0 microns (about 0.0005 and 0.001 inch). However, to provide the thermal stress relief mentioned previously, when using C-4 as the interconnections 16, it is preferred that the polyimide not have a thickness greater than approximately 25.0 microns (about 0.001 inch). When using other types of interconnections 16, it may be feasible, and desirable in certain situations, to use a thicker polyimide layer 2. For example, if a thermal compression bonding technique is used to make the interconnections 16, then the polyimide layer 2 may have a thickness of up to approxi-

mately 128.2 microns (about 0.005 inch).

There may be a preferred width and length for the polyimide forming the flexible film 2 depending on the capabilities of the equipment available for handling the film 2. Otherwise, the polyimide forming the flexible film 2 may virtually have any desired width and length which is reasonable from the viewpoint of handling the flexible film 2.

The polyimide forming the flexible film 2 may be any one of a number of specific materials. For example, "5878" polyimide (PMDA-ODA type) available from E. I. Du Pont de Nemours and Company may be used. This "5878" polyimide is a thermo set condensation polymer polyimide, which is basically a high temperature, elastic material. That is, it is capable of withstanding processing temperatures up to approximately 400 degrees centigrade, and may be stretched.

Preferably, the circuitry 10 on the flexible film 2 is relatively fine line circuitry with the individual circuit lines 10 having a thickness (height) of approximately 7.6 microns (about 0.0003 inch) and a width of approximately 25.4 microns (about 0.001 inch). However, it should be noted that the thickness and width of the circuit lines 10 may vary depending on factors such as the capabilities of the process used to form the circuitry on the flexible film 2, the planned use for the circuitry, and the performance characteristics expected of the circuitry and of the resulting full panel, circuitized flexible film 2.

Preferably, each of the filled heat conducting vias 19 in the flexible film 2 is a cylindrical structure having a diameter between approximately 256.4 microns (about 0.010 inch) and 512.8 microns (about 0.020 inch). The filled heat conducting vias 19 may be formed by electrolytic or electroless plating, sputtering, screening, or other such suitable process.

As shown in Figure 3, the circuitry 10 on the flexible film 2 is patterned to provide six sites for mounting the semiconductor chips 4 on the circuitized flexible film 2 and for connecting the semiconductor chips 4 to the circuitry 10 on the circuit board 6. However, the circuitry 10 on the flexible film 2 may have virtually any desired pattern and may also provide electrical connections between the different semiconductor chips 4 mounted on the circuitized flexible film 2.

Preferably, the circuitry on the flexible film 2 comprises a chromium-copper-chromium (Cr-Cu-Cr) metallurgical system which is personalized using photolithographic and etching techniques such as described in United States Patents 4,231,154, 4,480,288, and 4,517,051, assigned to International Business Machines Corporation, Armonk, New York, the disclosures of which are incorporated herein by this reference. Although, for ease of

illustration, Figures 2 and 3 show circuitry only on one side of the flexible film 2, if desired, the flexible film 2 may have circuitry on both sides with interconnecting vias as described, for example, in the previously mentioned United States Patents 4,480,288 and 4,517,051.

Preferably, the frame 8 for the full panel, circuitized flexible film 2 is made of a heat conductive material such as aluminum. As shown in Figures 1, 2, and 3, the frame 8 is rectangular and is attached to the edges of the full panel, circuitized flexible film 2. The frame 8 may include slots and/or notches (not shown) for registration of the frame 8 during manufacture of the circuitized flexible film 2 on the frame. Preferably, for use with a flexible film 2 having a width of approximately 177.8 millimeters (about 7 inches) and a length of approximately 228.6 millimeters (about 9 inches), the frame 8 is approximately 12.7 to 25.4 millimeters (about 0.5 to 1.0 inch) wide, and approximately 0.77 millimeters (about 0.030 inch) thick. If desired, the frame 8 may be configured in a "windowpane", or other such, structure with each "pane" of the frame 8 surrounding one of the areas of the flexible film 2 on which one of the semiconductor chips 4 is to be mounted. However, it should be noted that, in general, the frame 8 may have any one of a number of configurations depending on the equipment available for handling the frame 8, the use which it is desired to make of the frame 8, and other such factors.

The primary function for the frame 8 is to facilitate handling of the full panel, circuitized flexible film 2 during its manufacture and during mounting of the circuitized flexible film 2 on the circuit board 6. For example, the frame 8 may be a part of a temporary full panel, planar support on which the full panel, circuitized flexible film 2 is made. Then, all of the full panel, planar support, except for the frame 8, may be removed by a suitable process such as an etching process. For example, if the temporary full panel, planar support is made of aluminum, then hydrochloric acid can be used as an etchant, with a wax etchant mask protecting that part of the planar support which is to remain as the frame 8.

The frame 8 may also be used to transfer heat from the semiconductor chips 4 mounted on the circuitized flexible film 2 to the heat sink 20 which is part of the circuit board 6. Figure 2 shows one way the frame 8 may be placed in thermal contact with the heat sink 20 of the circuit board 6 through the vias 19 filled with a heat conductive material, such as copper. Also, if desired, to enhance heat transfer between the semiconductor chips 4 and the frame 8, heat conducting circuit lines (not shown), which are electrically non-functional, may be used to thermally interconnect electrically non-

functional terminals 18 of the semiconductor chips 4 to the frame 8 through selected ones of the heat conducting vias 19. These heat conducting circuit lines may be formed on the flexible film 2 at the same time as the circuit lines 10 are formed on the film 2.

Preferably, the heat sink 20 is a layer of a heat conductive material, such as copper, formed on the top surface of the printed circuit board 6 in a rectangular strip having approximately the same width as the frame 8 and having a thickness of approximately 35.9 microns (about 0.0014 inch). The heat sink 20 may be formed at the same time, and in the same manner, as the circuit lines 12 on the printed circuit board 6. The frame 8 with the heat conducting vias 19 may be attached to the heat sink 20 at the same time, and in the same manner, as the circuitized flexible film 2 with the semiconductor chips 4 is mounted on the circuit board 6.

Alternatively, in lieu of, or in addition to, using the frame 8 to transfer heat from the semiconductor chips 4 mounted on the circuitized flexible film 2 to the heat sink 20, and/or to the printed circuit board 6, heat conductive studs (not shown) may be formed in the printed circuit board 6 at locations beneath the semiconductor chips 4 such that, when the flexible film 2 with the semiconductor chips 4 is mounted on the printed circuit board 6, the heat conductive studs are in thermal contact with the tops of the semiconductor chips 4 which are facing the top surface of the printed circuit board 6.

Although Figures 1-3 show semiconductor chips 4 mounted on the circuitry 10 of the flexible film 2, it should be noted that, if desired, other kinds of electronic devices may be mounted on the circuitry 10 of the flexible film 2. For example, capacitors, resistors, and/or other such devices, may be mounted on some or all of the semiconductor chip mounting sites on the circuitized flexible film 2. Also, it should be noted that, if desired, the flexible film 2 may simply have circuitry 10 thereon, without any devices mounted thereto, such that the flexible film 2 with the circuitry 10 may be used as a cable, or "cross over", for interconnecting the circuit lines 12 on the printed circuit board 6 when the flexible film 2 with the circuitry 10 is mounted on the circuit board 6.

As shown in Figures 2 and 3, each of the semiconductor chips 4 is mounted on the circuitry 10 of the flexible film 2 using the interconnections 16 between the pads 21 on the flexible film 2 and the terminals 18 of the semiconductor chips 4. Preferably, the interconnections 16 are solder balls which are part of controlled collapse chip connections (C-4) for attaching each of the semiconductor chips 4 to the circuitry 10 on the flexible film 2 in an area or peripheral array attachment configura-

tion. However, if desired, other techniques, such as thermal compression bonding or ultrasonic bonding, may be used to mount the semiconductor chips 4, or other electronic devices, on the circuitry 10 of the flexible film 2.

Also, as shown in Figures 2 and 3, the interconnections 14 electrically and physically interconnect the lands 22 of the circuitry 10 of the flexible film 2 to the lands 24 of the circuitry 12 on the circuit board 6. Any suitable outer lead bonding technique may be used to make the interconnections 14. For example, the interconnections 14 may be made using a thermal compression bonding technique such as used in tape automated bonding (TAB).

As shown in Figures 1, 2 and 4, the circuitized flexible film 2 with the semiconductor chips 4 is shown mounted on a printed circuit board 6 made of a dielectric material such as glass cloth impregnated with epoxy resin. However, it should be noted that, if desired, the circuitized flexible film 2 with the semiconductor chips 4, or other electronic devices, may be mounted on any one of a number of different kinds of substrates, such as a ceramic, plastic, or other such substrate.

Preferably, the circuitry 12 on the circuit board 6 is formed using conventional photolithographic techniques. Each of the circuit lines 12 may be made of copper approximately 76 microns wide (about 0.003 inch), and having a thickness (height) of approximately 35.9 microns (about 0.0014 inch). For clarity and ease of illustration in Figures 2 and 4, only part of the circuitry 12 on the circuit board 6 is shown. It should be noted that the circuitry 12 may electrically interconnect some, none, or all of the semiconductor chips 4 on the circuit board 6, and, in general, may have any one of a variety of designs and configurations depending on the application for the electronic packaging structure 1. For example, if each of the circuit lines is approximately 76 microns wide (about 0.003 inch), then they may fan out in a grid having an approximately 250 microns (about 0.010 inch) separation between the circuit lines 12 at the semiconductor chip 4 bonding sites 25 to a grid having an approximately 1250 microns (about 0.050 inch), or an approximately 2500 microns (about 0.100 inch) separation between the circuit lines 12 at the locations on the circuit board 6 away from the bonding sites 25.

Preferably, according to the principles of the present invention, the previously described electronic packaging structure 1 is made by the following process. First, a flexible polymer film 2, such as the Du Pont "5878" polyimide mentioned previously, is applied to a panel of metal foil made of aluminum, copper, or other such material. The metal foil panel is sized to cover the circuit board 6, or other such substrate, on which the circuitized flexi-

ble film 2 is to be mounted. For example, the metal foil may be made a rectangular sheet of aluminum having a width of approximately 177.8 millimeters (about 7 inches), a length of approximately 228.6 millimeters (about 9 inches), and a thickness of approximately 127 microns (about 0.005 inch).

The polyimide may be applied to the metal foil by coating it on the foil in an uncured (unimidized) liquid form using a conventional spray, roller coater, or squeegee type application technique. However, any other suitable technique for applying the polyimide to the metal foil may be used, if desired.

The polyimide may be further processed directly on the metal foil or transferred to a full panel carrier frame using a transfer process such as described in EP-87105379.9, assigned to International Business Machines Corporation, entitled "Flexible Film Semiconductor Chip Carrier" which was filed on 10 April 1987, the entire disclosure of which is incorporated herein by this reference.

After the polyimide is applied to the metal foil or the carrier frame, it is fully cured (fully imidized) to a "C" stage, such that approximately 100% of the polyimide is imidized. For example, if the flexible polyimide film is the Du Pont "5878" polyimide which is to have a thickness of approximately 5.1 microns to 7.6 microns, then the liquid polyimide may be fully cured by heating at a temperature of approximately 360 to 400 degrees centigrade for approximately 30 minutes. If the polyimide is fully cured on the metal foil then the next step is to remove all of the metal foil except for that part of the foil forming the frame 8 for handling the flexible film 2. For example, the metal foil may be removed by etching in the presence of a wax etchant mask as described previously. Of course, if the polyimide is transferred to a carrier frame using the transfer process referenced above, the carrier frame used in this process is selected to have the configuration shown for the frame 8 in Figures 1, 3, and 4.

After the preceding steps, the fully cured polyimide flexible film 2 on the frame 8 is first metallized, then circuitized, and the semiconductor chips 4, or other such devices, are mounted on the circuitry 10 on the flexible film 2 as described previously. The semiconductor chips 4 may be mounted on the circuitized polyimide flexible film 2 by a conventional C-4 solder reflow process, or by any other such suitable process. The resulting structure is shown in Figure 3.

The semiconductor chips 4 may be tested and "burned in" while the circuitized, polyimide flexible film 2 is still in the frame 8 before this structure is mounted on the circuit board 6. That is, the chips 4, and the circuit lines 10, may be electrically, or otherwise, tested to determine if there are any defects, and a known electric potential can be

applied through the circuit lines 10 on the flexible film 2 to selected terminals 18 of the semiconductor chips 4 to supply a desired electric current to the semiconductor chips 4 to perform a type of functional test of the semiconductor chips 4, known as "burn in".

Once the semiconductor chips 4 have been tested and burned in, and any defective chips 4 and/or circuit lines 10 have been located, then the circuitized flexible film 2 with the semiconductor chips 4 is mounted on the circuit board 6 having the bonding sites 25 matching the pattern of the semiconductor chips on the flexible film 2. Of course, if any of the chips 4 were found to be defective then the flexible film 2 is used with a circuit board 6 having functional bonding sites 25 which match up only with functional chips 4 on the circuitized flexible film 2. Alternatively, it may be possible to repair any defective chips 4 and/or circuitry 10 on the flexible film 2 before it is mounted on the circuit board 6. For example, a defective chip 4 may be removed (cut out) and replaced with a functional chip 4. This ability to identify defective chip sites before the flexible film 2 is mounted on the circuit board 6 is an effective way to ensure relatively high yields when manufacturing the electronic packaging structure 1 according to the principles of the present invention.

The circuitized flexible film 2 with the semiconductor chips 4 may be mounted on the printed circuit board 6 using any one of a number of techniques. For example, this flexible film 2 may be mounted on the circuit board 6 using commonly known backbonding and outer lead bonding techniques such as a thermal compression bonding technique used in tape automated bonding (TAB), or other such suitable outer lead bonding technique. Then the frame 8 may be removed from the flexible film 2 by, for example, cutting the frame away from the film 2. Alternatively, the frame 8 may be bonded to a heat sink 20 which is part of the circuit board 6 as described previously.

Several important features of the foregoing described electronic packaging structure 1 and the method for making such a structure 1, should be noted. First, this structure and method provide for relatively high yields when used in manufacturing electronic equipment, such as computers, especially when used in a relatively high volume manufacturing environment. High yield is provided for since the chip sites on the full panel, circuitized flexible film 2 can be standardized for use with any one of a number of different circuit boards 6 designed for using only certain selected chips 4 on the circuitized flexible film 2. Thus, a given circuitized flexible film 2 with semiconductor chips 4 may still be used even if one or more of the chip sites are found to be defective since it may be

possible to match the semiconductor chips 4 on the circuitized flexible film 2 with a circuit board 6 which does not need to use the chip site(s) found to be defective.

Also, the packaging structure 1 and method for making such a structure 1 according to the present invention, provide for handling many semiconductor chips 4, or other such electronic devices, at once. That is, several semiconductor chips 4 may be handled at the same time on one full panel, circuitized flexible film 2. This feature of the present invention is very important since it can increase productivity, reduce manufacturing costs, and, in general, make it easier to manufacture electronic equipment, such as computers, especially when it is desired to manufacture such equipment in a relatively high volume manufacturing environment. For example, when handling a full panel of semiconductor chips 4 which are to be mounted on a circuit board 6, the entire panel of the semiconductor chips 4 may be aligned, and placed in registration, with the circuit board 6, in one operation. This eliminates the need to individually align, and place in registration, each of the semiconductor chips 4 with respect to its matching bonding site 25 on the circuit board 6, which otherwise would be necessary if a single chip handling type manufacturing technique was used.

## Claims

1. An electronic packaging structure (1) comprising:

a circuitized substrate (6) having a plurality of bonding sites arranged in a selected pattern on said circuitized substrate; and

a flexible film chip carrier (2) with circuitry connected to a plurality of electronic devices (4) mounted on said carrier in a pattern which matches the selected pattern of bonding sites on the circuitized substrate, said flexible film chip carrier mounted on the circuitized substrate with said electronic devices interconnected through said circuitry of said chip carrier to the the circuitry at the bonding sites of the circuitized substrate.

2. An electronic packaging structure as recited in claim 1 wherein said circuitized substrate comprises a printed circuit board (6) and/or

wherein each of said electronic devices comprises an integrated circuit chip (4).

3. An electronic packaging structure as recited in claim 1 or 2 wherein said flexible film chip carrier comprises:

a flexible layer (2) of polyimide with circuitry on at least one side of said polyimide layer, said circuitry including pads (21) on which the integrated circuit chips are mounted and lands interconnecting said circuitry on said polyimide layer to the circuitry on the circuitized substrate.

4. An electronic packaging structure as recited in claim 3 wherein said flexible layer of polyimide comprises a sheet of polyimide having a thickness between approximately 5.1 microns (about 0.0002 inch) and 7.6 microns (about 0.0003 inch).

5. An electronic packaging structure as recited in one of the claims 1 - 4 wherein said circuitized substrate includes at least one heat sink (20).

6. An electronic packaging structure as recited in claim 5 wherein said flexible film chip carrier includes a thermally conductive frame (8) in thermal contact with the heat sink of the circuitized substrate.

7. A method for making an electronic packaging structure comprising the steps of:

fabricating a substrate (6) with circuitry having a plurality of bonding sites arranged in a selected pattern;

forming a layer (2) of flexible film on a support structure, said flexible film being sized and configured to cover the bonding sites of the circuitized substrate when said flexible film is mounted on the circuitized substrate;

circuitizing the flexible film on the support structure with a circuit pattern having a plurality of device attachment sites matching the selected pattern of bonding sites on the circuitized substrate;

attaching a selected electronic device (4) to each of the device attachment sites of the circuitry on the flexible film; and

mounting the circuitized, flexible film, with the electronic devices attached thereto, on the circuitized substrate whereby each of the electronic devices attached to the circuitized, flexible film, is interconnected through the circuitry on the flexible film to the circuitry at the matching bonding site on the circuitized substrate.

8. A method for making an electronic packaging structure as recited in claim 7 further comprising the step of:

testing each of the electronic devices attached to the circuitized, flexible film before this film is mounted on the circuitized substrate.

9. A method for making an electronic packaging structure as recited in claim 8 wherein the step of mounting the circuitized, flexible film, with

the electronic devices attached thereto, on the circuitized substrate comprises:

mounting the circuitized, flexible film with the electronic devices on a circuitized substrate having functional bonding sites matching only the electronic devices found to be functional after testing. 5

10. A method for making an electronic packaging structure as recited in claim 8 or 9 comprising the step of: 10

burning in each of the electronic devices attached to the circuitized, flexible film before this film is mounted on the circuitized substrate.

11. A method for making an electronic packaging structure as recited in one of the claims 7 - 10 further comprising the step of: 15

removing the support frame from the circuitized, flexible film after this film, with the electronic devices attached thereto, has been mounted on the circuitized substrate. 20

12. A method for making an electronic packaging structure as recited in one of the claims 7 - 11 wherein the step of attaching a selected electronic device to the circuitry on the flexible film comprises: 25

joining the electronic device to pads using a controlled collapse chip connection (C-4) technique. 30

13. A method for making an electronic packaging structure as recited in one of the claims 7 - 12 wherein the flexible film comprises a sheet of polyimide and the step of depositing metal comprises depositing successive layers of chromium, copper, and chromium on said sheet of polyimide. 35

40

45

50

55







FIG. 2







FIG. 3

FIG. 4



(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets

(11) Publication number:

**0 277 606  
A3**

(12)

**EUROPEAN PATENT APPLICATION**

(21) Application number: 88101320.5

(51) Int. Cl.4: **H01L 23/52 , H01L 25/04 ,  
H01L 21/60**

(22) Date of filing: 29.01.88

(30) Priority: 02.02.87 US 9981

(43) Date of publication of application:  
10.08.88 Bulletin 88/32(84) Designated Contracting States:  
DE FR GB IT(96) Date of deferred publication of the search report:  
08.03.89 Bulletin 89/10(71) Applicant: International Business Machines  
Corporation  
Old Orchard Road  
Armonk, N.Y. 10504(US)(72) Inventor: Gazdik, Charles Edward  
911 Westminster Road  
Endicott, N.Y. 13760(US)Inventor: McBride, Donald Gene  
2058 Cheshire Road

Binghamton, N.Y. 13903(US)

Inventor: Seraphim, Donald Phillip  
400 Rano Blvd.

Vestal, N.Y. 13850(US)

Inventor: Toole, Patrick Albert  
20 Harborview Rd.

Westport, CT 06880(US)


(74) Representative: Combeau, Jacques et al  
Compagnie IBM France Département de  
Propriété Intellectuelle  
F-06610 La Gaude(FR)

(54) Full panel electronic packaging structure and method of making same.

(57) An electronic packaging structure (1), and a method of making this structure, are disclosed. The electronic packaging structure comprises a full panel, circuitized flexible film semiconductor chip carrier (2) mounted on a circuitized substrate (6) such as a printed circuit board. A plurality of semiconductor chips (4) are mounted on the carrier in a selected pattern, and the carrier, with the chips, is mounted on a matching pattern of bonding sites on the circuitized substrate. Preferably, the circuitized flexible film semiconductor chip carrier is manufactured on a support structure used to facilitate handling of the circuitized flexible film and to facilitate heat transfer from the semiconductor chips mounted on the carrier to a heat sink (20) which is part of the circuitized substrate. Also, the semiconductor chips mounted on the flexible film chip carrier may be tested, and

burned in, while on the support structure before the chip carrier, with the chips, is mounted on the circuitized substrate.

FIG. 2


**EP 0 277 606 A3**



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number

EP 88 10 1320

## DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 4)
X	FR-A-2 382 101 (LABORATOIRES D'ELECTRONIQUE ET DE PHYSIQUE APPLIQUEE L.E.P.) * Page 3, lines 12-21; claims 1,2; figure 1 *	1-3,5	H 01 L 23/52 H 01 L 25/04 H 01 L 21/60
X	NEUES AUS DER TECHNIK, no. 3/4, 15th August 1984, page 2, Würzburg, DE; "Elektrisch-elektronische Einzelteile" * Whole document *	1,2	
A	US-A-4 251 852 (M.E. ECKER et al.) * Abstract; column 6, lines 25-33; claim 1; figures 1-3 *	1-3,7	
A	IBM TECHNICAL DISCLOSURE BULLETIN, vol. 25, no. 4, September 1982, pages 1954-1956, IBM Corp., New York, US; J.C. EDWARDS: "Chip attachment to tape and cable" * Whole document *	1,3,5	
A	PATENT ABSTRACTS OF JAPAN, vol. 6, no. 55 (E-101)[933], 10th April 1982; & JP-A-56 167 355 (NIPPON DENKI K.K.) 23-12-1981	1,5	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int. Cl. 4)
			H 01 L 23/00 H 05 K 1/00 H 01 L 25/00 H 05 K 3/00 H 01 L 21/00

Place of search

THE HAGUE

Date of completion of the search

12-12-1988

Examiner

DELPORTE B.P.M.

### CATEGORY OF CITED DOCUMENTS

X : particularly relevant if taken alone  
Y : particularly relevant if combined with another document of the same category  
A : technological background  
O : non-written disclosure  
P : intermediate document

T : theory or principle underlying the invention  
E : earlier patent document, but published on, or after the filing date  
D : document cited in the application  
L : document cited for other reasons

& : member of the same patent family, corresponding document